

|                    |          |                                    |
|--------------------|----------|------------------------------------|
| Quality            |          | : <b>LONDON</b>                    |
| Product definition |          | : tufted loop pile                 |
| Gauge              |          | : 1/8"                             |
| No. of tufts       | ISO 1763 | : ± 117000/m <sup>2</sup>          |
| Pile fibre         |          | : 100% polyamide SDN               |
| Pile weight        |          | : 520 gr/m <sup>2</sup> ± 5%       |
| Pile height        | ISO 1766 | : 3.5 mm ± 5%                      |
| Primary backing    |          | : PA/PES non-woven - Colback       |
| Tile backing       |          | : Polyflex with a non-woven fabric |
| Total thickness    | ISO 1765 | : 7.2 mm ± 7,5%                    |
| Total weight       |          | : 4200 gr/m <sup>2</sup> ± 7,5%    |
| Tile size          |          | : 50 x 50 cm (± 19.7" x 19.7")     |
| Tiles per box      |          | : 20                               |

**PERFORMANCE**

|                       |                      |                           |
|-----------------------|----------------------|---------------------------|
| Use classification    |                      | : Class 33                |
| Castor chair test     | EN 985               | : A, continues use        |
| Abrasion              | EN 1963              | : pass                    |
| Vettermann test       | ISO TR 10361/EN 1471 | : pass                    |
| Thermal isolation     | ISO 8302             | : 0.09 m <sup>2</sup> K/W |
| Dimensional stability | ISO 2551             | : pass                    |

**ELECTROSTATIC PROPERTIES**

|                                  |              |                       |
|----------------------------------|--------------|-----------------------|
| Walk on test                     | ISO 6356     | : -0.1 kV             |
| Horizontal electrical resistance | ISO CD 10965 | : 8x10 <sup>9</sup> Ω |
| Vertical electrical resistance   | ISO CD 10965 | : 4x10 <sup>9</sup> Ω |
| Static loading                   |              | : anti-static         |

**FLAME PROPERTIES**

|                    |                |                      |
|--------------------|----------------|----------------------|
| Reaction to fire   | EN ISO 11925-2 |                      |
|                    | EN ISO 9239-1  | : B <sub>n</sub> -s1 |
| Hot metal nut test | BS 4790        | : Low Radius         |

**COLOUR FASTNESS PROPERTIES**

|              |             |         |
|--------------|-------------|---------|
| Light        | ISO 105 B02 | : > 5.0 |
| Rubbing, dry | ISO 105 X12 | : 4.5   |
| Rubbing, wet | ISO 105 X12 | : 5.0   |
| Shampoo      | BS 1006     | : 4.5   |
| Water        | ISO 105 E01 | : 5.0   |
| Water stains | TNO W 6024  | : 5.0   |

**GENERAL**

Recommended maintenance:  
 Pile direction:

Best results are obtained when cleaned with a dry shampoo method.  
 Directional arrows are printed on the back of each tile.  
 Best results are obtained when laid checkerboard.

Laying instructions:

Tiles require no underlay, nailing, gluing or sewing and may be laid loose on a flat, dry, non-slippery floor. When tiles are laid on parquet, vinyl or in open areas larger than 30 m<sup>2</sup> it is advisable to use double sided adhesive tape on every 8th row or a tackifier.

**COLOURS**

|                   |                     |                 |               |
|-------------------|---------------------|-----------------|---------------|
| 1236<br>Blue      | 1237<br>Seablue     | 1265<br>Red     | 1205<br>Azuur |
| 1280<br>Blue grey | 1283<br>Marine blue | 1276<br>D. grey | 1290<br>Beige |
| 1279<br>Black     | 1278<br>Charcoal    | 1209<br>Earth   | 1208<br>Brown |

